

© Copyright SEK. Reproduction in any form without permission is prohibited.

## Bestämning av vissa ämnen i elektriska och elektroniska produkter – Del 2: Demontering, isärtagning och mekanisk provberedning

*Determination of certain substances in electrotechnical products –  
Part 2: Disassembly, disjointment and mechanical sample preparation*

Som svensk standard gäller europastandarden EN 62321-2:2014. Den svenska standarden innehåller den officiella engelska språkversionen av EN 62321-2:2014.

### Nationellt förord

Europastandarden EN 62321-2:2014

består av:

- **europastandardens ikraftsättningsdokument**, utarbetat inom CENELEC
- **IEC 62321-2, First edition, 2013 - Determination of certain substances in electrotechnical products - Part 2: Disassembly, disjointment and mechanical sample preparation**

utarbetad inom International Electrotechnical Commission, IEC.

Tidigare fastställd svensk standard SS-EN 62321, utgåva 1, 2009 gäller ej 2016-11-15.

Standarden ersätter avsnitt 5 i SS-EN 62321, utgåva 1, 2009.

### *Standarder underlättar utvecklingen och höjer elsäkerheten*

Det finns många fördelar med att ha gemensamma tekniska regler för bl a säkerhet, prestanda, dokumentation, utförande och skötsel av elprodukter, elanläggningar och metoder. Genom att utforma sådana standarder blir säkerhetskraven tydliga och utvecklingskostnaderna rimliga samtidigt som marknadens acceptans för produkten eller tjänsten ökar.

Många standarder inom elområdet beskriver tekniska lösningar och metoder som åstadkommer den elsäkerhet som föreskrivs av svenska myndigheter och av EU.

### *SEK är Sveriges röst i standardiseringsarbetet inom elområdet*

SEK Svensk Elstandard svarar för standardiseringen inom elområdet i Sverige och samordnar svensk medverkan i internationell och europeisk standardisering. SEK är en ideell organisation med frivilligt deltagande från svenska myndigheter, företag och organisationer som vill medverka till och påverka utformningen av tekniska regler inom elektrotekniken.

SEK samordnar svenska intressenters medverkan i SEKs tekniska kommittéer och stödjer svenska experters medverkan i internationella och europeiska projekt.

### *Stora delar av arbetet sker internationellt*

Utformningen av standarder sker i allt väsentligt i internationellt och europeiskt samarbete. SEK är svensk nationalkommitté av International Electrotechnical Commission (IEC) och Comité Européen de Normalisation Electrotechnique (CENELEC).

Standardiseringsarbetet inom SEK är organiserat i referensgrupper bestående av ett antal tekniska kommittéer som speglar hur arbetet inom IEC och CENELEC är organiserat.

Arbetet i de tekniska kommittéerna är öppet för alla svenska organisationer, företag, institutioner, myndigheter och statliga verk. Den årliga avgiften för deltagandet och intäkter från försäljning finansierar SEKs standardiseringsverksamhet och medlemsavgift till IEC och CENELEC.

### *Var med och påverka!*

Den som deltar i SEKs tekniska kommittéarbete har möjlighet att påverka framtida standarder och får tidig tillgång till information och dokumentation om utvecklingen inom sitt teknikområde. Arbetet och kontakterna med kollegor, kunder och konkurrenter kan gynnsamt påverka enskilda företags affärsutveckling och bidrar till deltagarnas egen kompetensutveckling.

Du som vill dra nytta av dessa möjligheter är välkommen att kontakta SEKs kansli för mer information.

### **SEK Svensk Elstandard**

Box 1284  
164 29 Kista  
Tel 08-444 14 00  
[www.elstandard.se](http://www.elstandard.se)

English version

**Determination of certain substances in electrotechnical products -  
Part 2: Disassembly, disjointment and mechanical sample preparation  
(IEC 62321-2:2013)**

Détermination de certaines substances  
dans les produits électrotechniques -  
Partie 2: Démontage, désassemblage et  
préparation mécanique de l'échantillon  
(CEI 62321-2:2013)

Verfahren zur Bestimmung von  
bestimmten Substanzen in Produkten der  
Elektrotechnik -  
Teil 2: Demontage, Zerlegung und  
mechanische Probenvorbereitung  
(IEC 62321-2:2013)

This European Standard was approved by CENELEC on 2013-11-15. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**CENELEC**

European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**CEN-CENELEC Management Centre: Avenue Marnix 17, B - 1000 Brussels**

## Foreword

The text of document 111/301/FDIS, future edition 1 of IEC 62321-2, prepared by IEC/TC 111 "Environmental standardization for electrical and electronic products and systems" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 62321-2:2014.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2014-10-25
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2016-11-15

EN 62321-2:2014 is a partial replacement of EN 62321:2009, forming a structural revision and generally replacing Clause 5 and incorporating IEC/PAS 62596:2009 [1]<sup>1)</sup> which will be withdrawn upon publication of IEC 62321-2.

Future parts in the EN 62321 series will gradually replace the corresponding clauses in EN 62321:2009. Until such time as all parts are published, however, EN 62321:2009 remains valid for those clauses not yet re-published as a separate part.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

## Endorsement notice

The text of the International Standard IEC 62321-2:2013 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 62554	NOTE	Harmonised as EN 62554 (not modified).
IEC 62542	NOTE	Harmonised as EN 62542 (not modified).
IEC 62321-6	NOTE	Harmonised as EN 62321-6 (not modified).
IEC 62321-7-1	NOTE	Harmonised as EN 62321-7-1 (not modified).
IEC 62137-1-2	NOTE	Harmonised as EN 62137-1-2 (not modified).

---

<sup>1)</sup> Numbers in square brackets refer to the Bibliography.

## Annex ZA (normative)

### Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 62321-1	-	Determination of certain substances in electrotechnical products - Part 1: Introduction and overview	EN 62321-1	-
IEC 62321-3-1	-	Determination of certain substances in electrotechnical products - Part 3-1: Screening electrotechnical products for lead, mercury, cadmium, total chromium and total bromine using X-ray Fluorescence Spectrometry	EN 62321-3-1	-
IEC 62321-3-2	-	Determination of certain substances in electrotechnical products - Part 3-2: Screening of total bromine in electric and electronic products by combustion-ion chromatography (C-IC)	EN 62321-3-2	-
IEC 62321-4	-	Determination of certain substances in electrotechnical products - Part 4: Determination of mercury in polymers, metals and electronics by CV-AAS, CV-AFS, ICP-OES and ICP-MS	EN 62321-4	-
IEC 62321-5	-	Determination of certain substances in electrotechnical products - Part 5: Determination of cadmium, lead and chromium in polymers and electronics, and cadmium and lead in metals by AAS, AFS, ICP-OES and ICP-MS	EN 62321-5	-

## CONTENTS

INTRODUCTION.....	6
1 Scope.....	7
2 Normative references .....	7
3 Terms, definitions and abbreviations .....	8
3.1 Terms and definitions .....	8
3.2 Abbreviations .....	8
4 Introduction to sampling .....	9
4.1 Introductory remark .....	9
4.2 Requirements and concerns for substances of concern .....	9
4.3 Complexity of electrotechnical products and related challenges.....	9
4.4 Strategies for sampling.....	10
5 Sampling .....	13
5.1 Introductory remark .....	13
5.2 Complete product .....	14
5.3 Partial disassembly .....	14
5.4 Complete disassembly.....	14
5.5 Partial disjointment.....	14
5.6 Complete disjointment.....	15
5.7 Considerations of sampling and disjointment.....	15
5.7.1 Introductory remark .....	15
5.7.2 Sample size required .....	15
5.7.3 Sample size versus detection limit.....	17
5.7.4 Composite testing of disjointable samples .....	17
5.7.5 Non-uniform “homogeneous materials” .....	18
5.7.6 Determination of sampling position of homogeneous materials .....	19
6 Conclusions and recommendations for sampling .....	19
7 Mechanical sample preparation .....	20
7.1 Overview .....	20
7.1.1 Field of application .....	20
7.1.2 Quality assurance.....	20
7.2 Apparatus, equipment and materials.....	21
7.3 Procedure .....	21
7.3.1 Manual cutting.....	21
7.3.2 Coarse grinding/milling .....	22
7.3.3 Homogenizing.....	22
7.3.4 Fine grinding/milling .....	22
7.3.5 Very fine grinding of polymers and organic materials .....	22
Annex A (informative) Examples of procedures for sampling and disjointment .....	23
Annex B (informative) Probability of the presence of certain substances.....	32
Annex C (informative) Composite testing and sampling.....	35
Annex D (informative) Tools used in sampling.....	38
Annex E (informative) Examples of mobile phone disassembly and component disjointment .....	39
Bibliography.....	50

Figure 1 – Generic iterative procedure for sampling .....	11
Figure 2 – Cross-section of a 900 µm wide lead oxide-based resistor (SMD) .....	19
Figure A.1 – Methodology for sampling and disjointment.....	24
Figure A.2 – Sampling of DVD player .....	25
Figure A.3 – Sampling of CRT .....	26
Figure A.4 – Sampling of LCD TV .....	27
Figure A.5 – Sampling of PDA/phone .....	28
Figure A.6 – Sampling of desk fan .....	29
Figure A.7 – Sampling of components – Thick film resistor .....	30
Figure A.8 – Sampling of components – SMD potentiometer .....	31
Figure D.1 – Hot gas gun for removing the electronic components .....	38
Figure D.2 – Vacuum pin to remove the target electronic devices .....	38
Figure E.1 – Mobile phone type A with battery charger and camera lens cap .....	39
Figure E.2 – Mobile phone type A with battery and back cover removed .....	40
Figure E.3 – Partial disassembly of a mobile phone (type B) into its major components .....	41
Figure E.4 – Complete disassembly of the key pad .....	42
Figure E.5 – Complete disassembly of the bottom housing .....	42
Figure E.6 – Complete disassembly of the other housing/frame .....	43
Figure E.7 – Components of the TFT display of the mobile phone after partial disjointment .....	43
Figure E.8 – Components of the main PWB of the mobile phone after partial disjointment .....	44
Figure E.9 – Disjointment of lead frame component .....	46
Figure E.10 – BGA package prior to disjointment .....	47
Figure E.11 – BGA package disjointed by the hand removal procedure .....	47
Figure E.12 – Solder ball material collected from BGA using a hand removal procedure .....	48
Figure E.13 – BGA solder ball removal using the ball shear procedure .....	48
Table 1 – Minimum number of lead frame samples required for analytical testing .....	16
Table 2 – Levels of a certain substance in a composite sample .....	18
Table B.1 – Probability of the presence of certain substances in materials and components used in electrotechnical products (1 of 3) .....	32
Table C.1 – Calculated maximum concentration for a composite sample based on detection limit .....	36
Table C.2 – Required detection limit for a composite sample based on the maximum allowable concentration .....	37
Table E.1 – Possible certain substances or screening substances from a mobile phone .....	40
Table E.2 – Possible certain substances in major components of the mobile phone .....	41
Table E.3 – Examples of disjointment for typical small electronic components .....	45

## INTRODUCTION

The widespread use of electrotechnical products has drawn increased attention to their impact on the environment. In many countries this has resulted in the adaptation of regulations affecting wastes, substances and energy use of electrotechnical products.

The use of certain substances (e.g. lead (Pb), cadmium (Cd) and polybrominated diphenyl ethers (PBDEs)) in electrotechnical products, is a source of concern in current and proposed regional legislation.

The purpose of the IEC 62321 series is therefore to provide test methods that will allow the electrotechnical industry to determine the levels of certain substances of concern in electrotechnical products on a consistent global basis.

**WARNING – Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.**



## DETERMINATION OF CERTAIN SUBSTANCES IN ELECTROTECHNICAL PRODUCTS –

### Part 2: Disassembly, disjointment and mechanical sample preparation

#### 1 Scope

This part of IEC 62321 provides strategies of sampling along with the mechanical preparation of samples from electrotechnical products, electronic assemblies and electronic components. These samples can be used for analytical testing to determine the levels of certain substances as described in the test methods in other parts of IEC 62321. Restrictions for substances will vary between geographic regions and from time to time. This Standard describes a generic process for obtaining and preparing samples prior to the determination of any substance which are under concern.

This standard does not provide:

- full guidance on each and every product that could be classified as electrotechnical equipment. Since there is a huge variety of electrotechnical components, with various structures and processes, along with the continuous innovations in the industry, it is unrealistic to attempt to provide procedures for the disjointment of every type of component;
- guidance regarding other routes to gather additional information on certain substances in a product, although the information collected has relevance to the sampling strategies in this standard;
- safe disassembly and mechanical disjointment instructions related to electrotechnical products (e.g. mercury-containing switches) and the recycling industry (e.g. how to handle CRTs or the safe removal of batteries). See IEC 62554 [2] for the disjointment and mechanical sample preparation of mercury-containing fluorescent lamps;
- the definition of a “unit” as the sample;
- sampling procedures for packaging and packaging materials;
- analytical procedures to measure the levels of certain substances. This is covered by other standards (for example other parts of IEC 62321), which are referred to as the “test standard” in this standard;
- guidelines for assessment of compliance.

NOTE Further guidance on assessment procedures is provided by IEC/TR 62476 [3].

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62321-1, *Determination of certain substances in electrotechnical products – Part 1 Introduction and overview*

IEC 62321-3-1, *Determination of certain substances in electrotechnical products – Part 3-1: Screening – Lead, mercury, cadmium, total chromium and total bromine using X-ray fluorescence spectrometry*

IEC 62321-3-2, *Determination of certain substances in electrotechnical products – Part 3-2: Screening – Total bromine in polymers and electronics by combustion – Ion chromatography (C-IC)*

IEC 62321-4, *Determination of certain substances in electrotechnical products – Part 4: Determination of mercury in polymers, metals and electronics by CV-AAS, CV-AFS, ICP-OES and ICP-MS*

IEC 62321-5, *Determination of certain substances in electrotechnical products – Part 5: Determination of cadmium, lead and chromium in polymers and electronics and cadmium and lead in metals by AAS, AFS, ICP-OES, ICP-AES and ICP-MS<sup>2</sup>*