

© Copyright SEK. Reproduction in any form without permission is prohibited.

Optofibrer – Del 1-33: Mätning och provning – Spänningskorrosion (mekanisk påkänning)

Optical fibres –

Part 1-33: Measurement methods and test procedures –

Stress corrosion susceptibility

Som svensk standard gäller europastandarden EN 60793-1-33:2002. Den svenska standarden innehåller den officiella engelska språkversionen av EN 60793-1-33:2002.

Nationellt förord

Europastandarden EN 60793-1-33:2002^{*)}

består av:

- **europastandardens ikraftsättningsdokument**, utarbetat inom CENELEC
- **IEC 60793-1-33, First edition, 2001 - Optical fibres - Part 1-33: Measurement methods and test procedures - Stress corrosion susceptibility**

utarbetad inom International Electrotechnical Commission, IEC.

^{*)} EN 60793-1-33:2002 ikraftsattes 2004-04-26 som SS-EN 60793-1-33 genom offentliggörande, d v s utan utgivning av något svenskt dokument.

Standarder underlättar utvecklingen och höjer elsäkerheten

Det finns många fördelar med att ha gemensamma tekniska regler för bl a mätning, säkerhet och provning och för utförande, skötsel och dokumentation av elprodukter och elanläggningar.

Genom att utforma sådana standarder blir säkerhetsfordringar tydliga och utvecklingskostnaderna rimliga samtidigt som marknadens acceptans för produkten eller tjänsten ökar.

Många standarder inom elområdet beskriver tekniska lösningar och metoder som åstadkommer den elsäkerhet som föreskrivs av svenska myndigheter och av EU.

SEK är Sveriges röst i standardiseringsarbetet inom elområdet

SEK Svensk Elstandard svarar för standardiseringen inom elområdet i Sverige och samordnar svensk medverkan i internationell och europeisk standardisering. SEK är en ideell organisation med frivilligt deltagande från svenska myndigheter, företag och organisationer som vill medverka till och påverka utformningen av tekniska regler inom elektrotekniken.

SEK samordnar svenska intressenters medverkan i SEKs tekniska kommittéer och stödjer svenska experters medverkan i internationella och europeiska projekt.

Stora delar av arbetet sker internationellt

Utformningen av standarder sker i allt väsentligt i internationellt och europeiskt samarbete. SEK är svensk nationalkommitté av International Electrotechnical Commission (IEC) och Comité Européen de Normalisation Electrotechnique (CENELEC).

Standardiseringsarbetet inom SEK är organiserat i referensgrupper bestående av ett antal tekniska kommittéer som speglar hur arbetet inom IEC och CENELEC är organiserat.

Arbetet i de tekniska kommittéerna är öppet för alla svenska organisationer, företag, institutioner, myndigheter och statliga verk. Den årliga avgiften för deltagandet och intäkter från försäljning finansierar SEKs standardiseringsverksamhet och medlemsavgift till IEC och CENELEC.

Var med och påverka!

Den som deltar i SEKs tekniska kommittéarbete har möjlighet att påverka framtida standarder och får tidig tillgång till information och dokumentation om utvecklingen inom sitt teknikområde. Arbetet och kontakterna med kollegor, kunder och konkurrenter kan gynnsamt påverka enskilda företags affärsutveckling och bidrar till deltagarnas egen kompetensutveckling.

Du som vill dra nytta av dessa möjligheter är välkommen att kontakta SEKs kansli för mer information.

SEK Svensk Elstandard

Box 1284
164 29 Kista
Tel 08-444 14 00
www.elstandard.se

Optical fibres
Part 1-33: Measurement methods and test procedures -
Stress corrosion susceptibility
(IEC 60793-1-33:2001)

Fibres optiques
Partie 1-33: Méthodes de mesure
et procédures d'essai -
Résistance à la corrosion sous contrainte
(CEI 60793-1-33:2001)

Lichtwellenleiter
Teil 1-33: Messmethoden
und Prüfverfahren -
Spannungskorrosionsempfindlichkeit
(IEC 60793-1-33:2001)

This European Standard was approved by CENELEC on 2002-03-05. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 86A/688/FDIS, future edition 1 of IEC 60793-1-33, prepared by SC 86A, Fibres and cables, of IEC TC 86, Fibre optics, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 60793-1-33 on 2002-03-05.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2002-12-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2005-03-01

Annexes designated "normative" are part of the body of the standard.

Annexes designated "informative" are given for information only.

In this standard, annexes A, B, C, D, E and ZA are normative and annexes F, G and H are informative.

Annex ZA has been added by CENELEC.

Compared to IEC 60793-1:1989 and IEC 60793-2:1992, IEC/SC 86A has adopted a revised structure of the new IEC 60793 series: The individual measurement methods and test procedures for optical fibres are published as "Part 1-XX"; the product standards are published as "Part 2-XX".

The general relationship between the new series of EN 60793 and the superseded European Standards of the EN 188000 series is as follows:

EN	Title	supersedes
EN 60793-1-XX	Optical fibres -- Part 1-XX: Measurement methods and test procedures	Individual subclauses of EN 188000:1992
EN 60793-2-XX	Optical fibres -- Part 2-XX: Product specifications	EN 188100:1995 EN 188101:1995 EN 188102:1995 EN 188200:1995 EN 188201:1995 EN 188202:1995

EN 60793-1-3X consists of the following parts, under the general title: Optical fibres:

- Part 1-30: Measurement methods and test procedures – Fibre proof test
- Part 1-31: Measurement methods and test procedures – Tensile strength
- Part 1-32: Measurement methods and test procedures – Coating strippability
- Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility
- Part 1-34: Measurement methods and test procedures – Fibre curl

Endorsement notice

The text of the International Standard IEC 60793-1-33:2001 was approved by CENELEC as a European Standard without any modification.

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC/TR 62048	- ¹⁾	The law theory of optical fibre reliability	-	-

¹⁾ To be published.

CONTENTS

FOREWORD.....	5
INTRODUCTION.....	9
1 Scope and object.....	11
2 Normative references	11
3 Apparatus.....	13
4 Sampling and specimens	13
5 Reference test method	13
6 Procedure.....	15
7 Calculations	15
8 Results	15
9 Specification information	15
Annex A (normative) Dynamic n value by axial tension	17
Annex B (normative) Dynamic n value by two-point bending	31
Annex C (normative) Static n value by axial tension	41
Annex D (normative) Static n value by two-point bending.....	47
Annex E (normative) Static n value by uniform bending.....	51
Annex F (informative) Considerations for dynamic fatigue calculations	57
Annex G (informative) Considerations for static fatigue calculations	65
Annex H (informative) Considerations on stress corrosion susceptibility parameter test methods	67
Bibliography.....	75
Figure A.1 – Schematic of translation test apparatus	17
Figure A.2 – Schematic of rotational test apparatus	19
Figure A.3 – Schematic of rotational test apparatus with load cell	19
Figure A.4 – Representation of dynamic fatigue graph	29
Figure B.1 – Schematic of two-point bending unit.....	37
Figure B.2 – Schematic of surface platen.....	39
Figure B.3 – Dynamic fatigue data schematic.....	39
Figure C.1 – Schematic of possible static fatigue (tension) apparatus	45
Figure D.1 – Schematic of possible static fatigue (two-point bending) apparatus	49
Figure E.1 – Schematic of possible static fatigue (uniform bending) apparatus	55
Figure H.1 – The results of the round robin fracture strength versus time.....	73
Figure H.2 – The results of the round robin fracture strength versus time.....	73
Table F.1 – 95 % confidence interval for n_d	59

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 1-33: Measurement methods and test procedures –
Stress corrosion susceptibility**

FOREWORD

- 1) The IEC (International Electrotechnical Commission) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of the IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, the IEC publishes International Standards. Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. The IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of the IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested National Committees.
- 3) The documents produced have the form of recommendations for international use and are published in the form of standards, technical specifications, technical reports or guides and they are accepted by the National Committees in that sense.
- 4) In order to promote international unification, IEC National Committees undertake to apply IEC International Standards transparently to the maximum extent possible in their national and regional standards. Any divergence between the IEC Standard and the corresponding national or regional standard shall be clearly indicated in the latter.
- 4) The IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with one of its standards.
- 5) Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. The IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-33 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This standard, together with the other standards in the IEC 60793-1-3X series, cancels and replaces the second edition of IEC 60793-1-3, of which it constitutes a technical revision.

The text of this standard is based on the following documents:

FDIS	Report on voting
86A/688/FDIS	86A/727/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

Annexes A, B, C, D, E form an integral part of this standard.

Annexes F, G, H are for information only.

IEC 60793-1-3X consists of the following parts, under the general title *Optical fibres*:

- Part 1-30: Measurement methods and test procedures: Fibre proof test
- Part 1-31: Measurement methods and test procedures: Tensile strength
- Part 1-32: Measurement methods and test procedures: Coating strippability
- Part 1-33: Measurement methods and test procedures: Stress corrosion susceptibility
- Part 1-34: Measurement methods and test procedures: Fibre curl

The committee has decided that the contents of this publication will remain unchanged until 2003. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

INTRODUCTION

Publications in the IEC 60793-1 series concern measurement methods and test procedures as they apply to optical fibres.

Within the same series several different areas are grouped, as follows:

- parts 1-10 to 1-19: General
- parts 1-20 to 1-29: Measurement methods and test procedures for dimensions
- parts 1-30 to 1-39: Measurement methods and test procedures for mechanical characteristics
- parts 1-40 to 1-49: Measurement methods and test procedures for transmission and optical characteristics
- parts 1-50 to 1-59: Measurement methods and test procedures for environmental characteristics.

OPTICAL FIBRES –

Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility

1 Scope and object

This part of IEC 60793 contains descriptions of the five main test methods concerning the determination of stress corrosion susceptibility parameters.

The object of this standard is to establish uniform requirements for the mechanical characteristic stress corrosion susceptibility. Dynamic fatigue and static fatigue tests are used in practice to determine stress corrosion susceptibility parameters, dynamic n -value and static n -value.

Any fibre mechanical test should determine fracture stress and fatigue properties under conditions that model the practical application as close as possible. Some appropriate test methods are available:

- A: Dynamic n value by axial tension (see annex A);
- B: Dynamic n value by two-point bending (see annex B);
- C: Static n value by axial tension (see annex C);
- D: Static n value by two-point bending (see annex D);
- E: Static n value by uniform bending (see annex E).

These methods are appropriate for types A1, A2 and A3 multimode and type B1 single-mode fibres.

Static and dynamic fatigue test methods show comparable results if both tests are performed in the same effective measuring time. For dynamic fatigue tests this means a measuring time which is $(n + 1)$ times larger than the measuring time of static fatigue tests.

When using static fatigue test methods, it has been observed that for longer measuring times and consequently lower applied stress levels, the n -value increases. The range of measuring times of the static fatigue tests, given in this standard, approaches the practical situation better than that of the dynamic fatigue tests, which in general are performed in relatively short time-frames.

These tests provide values of the stress corrosion parameter, n , that can be used for reliability calculations according to IEC 62048.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62048, *The law theory of optical fibre reliability* ¹

¹ To be published.